


TARDEC



Technical Report

No. 13609

S

DTIC
ELECTE
JAN 03 1995

G

D

Evaluation of High Ester Content PAO Based Single Hydraulic Fluid in High Humidity Conditions

DTIC QUALITY INSPECTED 2

November 1994

19941230 000

By **Ellen M. Purdy**
USA Tank Automotive Command
Mobility Technology Center Belvoir

Distribution unlimited; approved for public release.



U.S. Army Tank-Automotive Command
Research, Development and Engineering Center
Warren, Michigan 48397-5000

The findings in this report are not to be construed as an official Department of the Army position unless so designated by other authorized documents.

Citation of manufacturer's or trade names does not constitute an official endorsement or approval of the use thereof.

Destroy this report when it is no longer needed. Do not return it to the originator.

REPORT DOCUMENTATION PAGE			Form Approved OMB No. 0704-0188	
Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.				
1. AGENCY USE ONLY (Leave blank)	2. REPORT DATE November 1994	3. REPORT TYPE AND DATES COVERED Final 1 Jun 93 - 31 Jul 93		
4. TITLE AND SUBTITLE Evaluation of High Ester Content PAO Based Single Hydraulic Fluid in High Humidity Conditions (U)		5. FUNDING NUMBERS PE 0602786A PR IL162786AH20 TA 0012 WU DA312114		
6. AUTHOR(S) Ellen M. Purdy		8. PERFORMING ORGANIZATION REPORT NUMBER TARDEC-TR-13609		
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) U.S. Army Tank-Automotive RD&E Center Mobility Technology Center, Fuels and Water Supply Division ATTN: AMSTA-RBFL Fort Belvoir, Virginia 22060-5606		10. SPONSORING/MONITORING AGENCY REPORT NUMBER		
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES)				
11. SUPPLEMENTARY NOTES				
12a. DISTRIBUTION/AVAILABILITY STATEMENT Distribution unlimited; approved for public release.			12b. DISTRIBUTION CODE	
13. ABSTRACT (Maximum 200 words) A Polyalphaolefin/Ester based Fire Resistant Hydraulic Fluid was subjected to high humidity conditions to determine water absorbance tendencies of the fluid. Fluid was subjected to 300 hours of humidification in an environment of 85% Relative Humidity. Four distinct fluid formulations containing ester contents of 34%-40% by weight were found to absorb no more than 0.25% water after the 300 hour period. A performance evaluation of the humidified fluid revealed no loss in performance regardless of the absorbed water present in the fluid. Because satisfactory performance was obtained, the hydraulic fluid formulations can contain up to 40% ester with no loss of performance. The increased ester content in the fluid formulations will provide sufficient seal swell for Army hydraulic systems that use the PAO based hydraulic fluid.				
14. SUBJECT TERMS			15. NUMBER OF PAGES 22	
			16. PRICE CODE	
17. SECURITY CLASSIFICATION OF REPORT Unclassified	18. SECURITY CLASSIFICATION OF THIS PAGE Unclassified	19. SECURITY CLASSIFICATION OF ABSTRACT Unclassified	20. LIMITATION OF ABSTRACT UL	

NSN 7540-01-280-5500

Standard Form 298 (Rev. 2-89)
Prescribed by ANSI Std. Z39-18
298-102

No. 13609

Evaluation of High Ester Content PAO Based Single Hydraulic Fluid in High Humidity Conditions

November 1994

Accession For	
NTIS	CRA&I <input checked="" type="checkbox"/>
DTIC	TAB <input type="checkbox"/>
Unannounced <input type="checkbox"/>	
Justification	
By	
Distribution /	
Availability Codes	
Dist	Avail and/or Special
A-1	

By **Ellen M. Purdy**
USA Tank Automotive Command
Mobility Technology Center Belvoir
Fuels and Lubricants Division

Contents

	Page
Section 1 Introduction	1
Section 2 Background.....	2
Section 3 Technical Approach	3
Section 4 Results	5
Section 5 Conclusions.....	8
References.....	9

Tables

1. SHF Formulations	3
2. Characterization & Performance Tests Baseline Results	3
3. Humidified Fluid Viscosities	5
4. Flash/Fire Point and Pour Point.....	5
5. Evaporation Loss for Humidified Fluids	6
6. Viscosity Change for Humidified Fluids.....	7

Figure

1. Water Absorption of SHF Formulations.....	4
--	---

Section I Introduction

The Army currently uses three military specification hydraulic fluids for its ground equipment; MIL-H-6083 (OHT); MIL-H-46170 (FRH); and MIL-H-5606 (OHA).^{1,2,3} In an attempt to decrease the logistic burden of using three distinct fluids, a single fluid was developed by the Belvoir Research, Development, and Engineering Center (BRDEC). The fluid is required to maintain the same level of fire resistance available from MIL-H-46170 (FRH), as well as provide the same level of low temperature operability and elastomer (seal) swell as MIL-H-5606 (OHA) and MIL-H-6083 (OHT), petroleum based hydraulic fluids which have relatively little fire resistance. Single hydraulic fluid (SHF), will use the same chemistry as FRH, but provide the same low temperature viscosities as OHA and OHT. Development of SHF is an attempt to provide the best of the three fluids while eliminating their deficiencies in one single fluid.

Section 2 Background

SHF is formulated primarily as a polyalphaolefin (PAO) and ester based fluid. The ester in the fluid formulation is intended to act as an elastomer swell agent. Traditionally, PAO based fire resistant hydraulic fluids are formulated with diesters with a limit of 30% by weight being the maximum allowed under MIL-H-46170. This limitation has been imposed due to the ester's propensity to absorb water from the atmosphere. This absorption of water increases the likelihood of corrosion and affects the low temperature viscosity. The 30% limit represents a compromise between the tendency of the fluid to absorb water and the amount of elastomer swell required by hydraulic systems sealing materials. Usually the ester in typical PAO/ester based fluids provide a volume swell for the standard NBR-L rubber of 15% - 19% which is used for qualification acceptance testing. There is a debate among hydraulic system users that this is insufficient elastomer swell to prevent excess leakage, and that the minimum amount of acceptable swell is 19%.^{4,5,6,7,8}

SHF requirements do not impose an ester content limit, but do require the minimum 19% elastomer swell. If a limit is to be included in the specification requirements for SHF, it will most likely be increased to 40% ester. To determine that this increased limit is not detrimental to fluid performance, formulations of varying ester contents were subjected to humidification then tested against the required performance targets for SHF.

Section 3 Technical Approach

Four formulations for SHF were prepared with ester contents varying from 34% to 40%. The ester used in these formulations is an isodecyl ester rather than a diester. Isodecyl esters were chosen for SHF because they do provide a significant level of elastomer swell, but also maintain high flash points and low viscosities at low temperatures. Typical viscosity values for these esters are 750 cSt at -54°C with a 170°C flash point. Diesters typically exhibit viscosities above 7,000 cSt at -54°C but have excellent flash points of 200°C or higher. The 4 formulations summarized in Table 1 below are formulations developed by the Fuels and Lubricants Division which successfully passed all SHF proposed performance requirements.⁹

Table 1. SHF Formulations

COMPONENT	SHF1	SHF2	SHF3	SHF4
% 2 cSt PAO Basestock	15	14.5	11.2	10.8
% 4 cSt PAO Basestock	45	43.5	44.8	43.2
% Isodecyl Ester	34	36	38	40
% Corrosion Inhibitor	3	3	3	3
% Anti-Wear Additive	2	2	2	2
% Antioxidant	1	1	1	1

The above formulations were tested against SHF performance requirements with results summarized in Table 2 below. The tests identified in Table 2 were deemed to be the fluid characteristics and/or performance most likely affected by excessive water absorption. This data establishes baseline performance against which the humidified fluid performance will be evaluated.

Table 2. Characterization & Performance Tests Baseline Results

Test	SHF1	SHF2	SHF3	SHF4
Flash Point	186°C	185°C	185°C	186°C
Fie Point	200°C	196°C	197°C	193°C
Pour Point	-65°C	-65°C	-65°C	-65°C
100°C Viscosity	2.56 cSt	2.57 cSt	2.59 cSt	2.56 cSt
40°C Viscosity	9.12 cSt	8.70 cSt	8.77 cSt	8.07 cSt
-40°C Viscosity	665 cSt	636 cSt	668 cSt	630 cSt
-54°C Viscosity	3427 cSt	3033 cSt	2887 cSt	2979 cSt
Low Temp Stability	pass	pass	pass	pass
Ox/Corr (FTM 5308)	pass	pass	pass	pass
Corrosion(hrs/hrs)*	272/336	248/240	214/377	272/336
Water Sensitivity	> 90%	> 90%	> 90%	> 90%
Evaporation Loss	33%	33%	30%	32%

*These values represent the number of hours before failure on a sandblasted surface (first number) and a polished surface (second number).

The 4 test fluids were subjected to humidification at 85% relative humidity with the water content determined daily (see Appendix A for humidification procedure).¹⁰ When an asymptotic rate of humidification was exhibited, the fluids were removed from the humidified environment for performance evaluation. Figure 1 shows the water absorption of the 4 SHF formulations. Over a total period of 288 hours, the maximum water content for the fluids never exceeded 0.25% water by weight. While the differences in water content among the four fluids are minimal, the formulation containing the highest amount of ester (40%) did exhibit the greatest water absorption.




Figure 1. Water Absorption of SHF Formulations

Section 4 Results

The viscosities of the humidified fluids are summarized in Table 3. Included in this table are the SHF performance targets. As can be seen, all of the fluids except SHF3 met the viscosity requirements for SHF even when humidified. The viscosities at the lower temperatures, although within requirements (except SHF3 at -54°C) are significantly greater than the baseline results. It would be expected that if the viscosity increases were due only to the additional amount of water in the fluids, SHF4 would exhibit the highest viscosity at the low temperatures, but such is not the case.

Table 3. Humidified Fluid Viscosities

FLUID	Viscosity (cSt)			
	40°C	100°C	-40°C	-54°C
SHF Requirement	19.5 max	2.5 min	800 max	3500 max
SHF1	8.62	2.58	710	3131
SHF2	8.88	2.57	702	3446
SHF3	8.80	2.54	702	3721
SHF4	8.74	2.57	695	3356

Flash point/fire point and pour point results are summarized in Table 4 along with the SHF target requirements. As can be seen, all 4 humidified formulations were well above the minimum flash/fire point requirements for SHF, but exhibited little difference from baseline data obtained from the non-humidified fluids.

Table 4. Flash/Fire Point and Pour Point

FLUID	FLASH	FIRE	POUR
SHF Requirement	180°C min	190°C min	-60°C min
SHF1	182°C	190°C	-66°C
SHF2	182°C	196°C	-66°C
SHF3	84°C	198°C	-66°C
SHF4	184°C	196°C	-66°C

Also no perceptible change in pour point was exhibited for the humidified fluids when compared to the non-humidified fluids.

One of the more critical tests performed on the humidified fluids involved low temperature stability. The humidified samples were subjected to -54°C for a period of 72 hours after which they were removed and examined for any signs of instability. Each of the fluids exhibited no signs of gelling, separation, or precipitation of additives. No

crystallization was present which was the most important criteria. Some synthetic fluids that absorb water will exhibit signs of crystallization indicating a separation of the water from the fluid at low temperatures. The humidified fluids provide the same stability at low temperatures as the unhumidified SHF.

Another significant test for synthetic hydraulic fluids involves light transmittance (see MIL-H-46170 for procedure). The percentage of light transmittance of a fluid is a measure of its sensitivity to water. This water sensitivity test was developed specifically to detect hydraulic fluid formulations which may contain water sensitive additive ingredients. The test involves doping 250 ml fluid samples with 0.5 ml of reagent grade water and allowing the fluids to sit for a period of 24 hours. An untreated sample is used to set the light transmittance standard at 100%, then the doped sample is tested. A fluid is considered sufficiently insensitive to water if the transmittance is 90% or greater. The humidified fluids exhibited transmittance rates between 96% and 100%, which further supports the stability of the high ester content formulations.

Evaporation Loss was tested for the humidified fluids. It was expected that if the fluids did pick up significant amounts of water, the evaporation loss would increase. As can be seen in Table 5, no significant change in evaporation occurred for the humidified fluids. This is not unusual since the greatest water content for the four test fluids was less than 0.25%.

Table 5. Evaporation Loss for Humidified Fluids

FLUID	SHF	SHF1	SHF2	SHF3	SHF4
% evaporation	35% max	31.6	32.0	31.1	30.6

Two final tests performed on the humidified fluids involve rust protection and oxidation/corrosion stability and are the two performance aspects which could be most significantly degraded by the presence of water. The humidity cabinet test is a severe test of a fluid's ability to inhibit corrosion. Steel panels which are polished on one side and sandblasted on another are subjected to a minimum 100 hours in the humidity cabinet. Failure occurs for each side when 3 rust spots greater than 1 mm in diameter appear. Each of the humidified fluids passed the 100 hour requirement but did exhibit a loss of protection due to the higher water content versus the un-humidified fluids. None of the fluid samples provided sufficient protection beyond 172 hours. This is a significant reduction in protection given that each of the un-humidified fluids provided at least 210 hours of protection.

The final test performed on the humidified fluids was Federal Test Method 791-5308 which was conducted for 168 hours (7 days) at 135°C (maximum operating temperature identified for SHF). The metal coupons of steel, magnesium, aluminum, cadmium, and copper showed no signs of oxidation or corrosion with minimal weight changes below the +0.2 mg/sqcm (+0.6 mg/sqcm for copper) requirement.

Table 6. Viscosity Change for Humidified Fluids

FLUID	Initial Vis	Final Vis	% Change
SHF1	8.62 cSt	9.69 cSt	12.41%
SHF2	8.88 cSt	9.66 cSt	8.78%
SHF3	8.80 cSt	9.44 cSt	7.27%
SHF4	8.74 cSt	9.35 cSt	6.98%

With the exception of SHF1, the humidified fluids exhibited acceptable viscosity changes of less than 10% (see Table 6), although the changes are somewhat higher than those normally exhibited by non-humidified fluids. The amount of water absorption does appear to have a slight affect on the viscosity change of the fluid, but the amount of ester does not seem to directly influence this change. SHF1 has the least amount of ester yet the greatest change in viscosity after being subjected to high humidity and the severe conditions of the FTM-791-5308 test.

Section 5 Conclusions

From the test results discussed above, it can be concluded that the use of isodecyl esters at treat rates between 34% and 40% do not adversely affect the fluid's performance. While water absorption does occur over time when the fluid is subjected to high humidity, very little water is actually picked up. Previous work in the development of these formulations reveals that ester contents of 34% to 40% provide elastomer swell for NBR-L rubber in the range of 19% to 22% which meets the requirements for SHF. Since the humidified fluids were able to perform satisfactory when evaluated against SHF requirements, there is no reason to limit the ester content to below 40%.

References

1. Military Specification: MIL-H-6083, *Hydraulic Fluid, Petroleum Base for Preservation and Operation*.
2. Military Specification: MIL-H-46170, *Hydraulic Fluid, Rust Inhibited, Fire Resistant, Synthetic Hydrocarbon Base*.
3. Military Specification: MIL-H-5606, *Hydraulic Fluid, Petroleum Base, Aircraft, Missile, and Ordinance*.
4. Final Letter Report on Product Improvement Test of Hydraulic Fluid (MIL-H-46170) in Turret Hydraulic Systems of M60A1 and M60A2 Tanks, TECOM Project No. 1-VC-08A-060-008, Report No. APG-MT-4853, August 1976.
5. Final Report, Initial Production Test of Automotive and Weapons Phase of M1A1 Tank System, TECOM Project No. 1-VC-080-1A1-004, Report No. USACSTA-6600, Volume I, March 1988, AD-B122693.
6. Current Production Test of Improved TOW Vehicle, M901, from TECOM Project No. 1-VC-030-901-003, APG Report No. APG-MT-5592, October 1981.
7. Contractor Report ARLCD-CR-79024, (TRW), AD-B044266, 1980.
8. "M140 Gun Mount Seal Degradation in MIL-H-46170 Hydraulic Fluid," Contractor Report ARSCD-CR-83015, November 1983, AD-B079-2791.
9. "Development of a Single Hydraulic Fluid for Use in Army Ground Equipment", BRDEC Technical Report No. , AD- , August 1993.
10. "Water Absorption of Fluids/Oils" Robert Jamison, Technical Report No. 2250, US Army Mobility Equipment Research and Development Command, June 1978.

Distribution for TARDEC Technical Report 13609 _____

DEPARTMENT OF THE ARMY

HQDA

1 ATTN DALO TSE
1 ATTN DALO SM
PENTAGON
WASHINGTON DC 20310-0103

CDR AMC

1 ATTN AMCRD S
1 ATTN AMCRD E
1 ATTN AMCRD IM
1 ATTN AMCRD IT
1 ATTN AMCRDA
1 ATTN AMCRD MS
1 ATTN AMCRD MT
1 ATTN AMCICP ISI
5001 EISENHOWER AVE
ALEXANDRIA VA 22333-0001

TARDEC

1 ATTN AMSTA CMA
1 ATTN AMSTA CMB
1 ATTN AMSTA CME
1 ATTN AMSTA N
1 ATTN AMSTA R
1 ATTN AMSTA RG
1 ATTN AMCPM ATP
1 ATTN AMSTA Q
1 ATTN AMSTA UE
1 ATTN AMSTA UG
CDR TACOM
WARREN MI 48397-5000

CDR ARMY TACOM

1 ATTN AMSTA FP
1 ATTN AMSTA KL
1 ATTN AMSTA MM
1 ATTN AMSTA MT
1 ATTN AMSTA MC
1 ATTN AMSTA GT
1 ATTN AMSTA FNG
1 ATTN AMSTA FR
1 ATTN USMC LNO
1 ATTN AMSPM LAV
1 ATTN AMSPM 113/M60
1 ATTN AMCPM CCE/SMHE
WARREN MI 48397-5000

CDR ARMY TACOM

20 ATTN AMSTA-RBF
10101 GRIDLEY RD STE 128
FT BELVOIR, VA 22060-5843

PROG EXEC OFFICER

ARMORED SYS MODERNIZATION

1 ATTN SFAE ASM S
1 ATTN SFAE ASM BV
1 ATTN SFAE ASM CV
1 ATTN SFAE ASM AG
CDR TACOM
WARREN MI 48397-5000

PROG EXEC OFFICER

ARMORED SYS MODERNIZATION

1 ATTN SFAE ASM FR
1 ATTN SFAE ASM AF
PICATINNY ARSENAL
NJ 07806-5000

PROG EXEC OFFICER

COMBAT SUPPORT

1 ATTN SFAE CS TVL
1 ATTN SFAE CS TVM
1 ATTN SFAE CS TVH
CDR TACOM
WARREN MI 48397-5000

PROG EXEC OFFICER

ARMAMENTS

1 ATTN SFAE AR HIP
1 ATTN SFAE AR TMA
1 PICATINNY ARSENAL
NJ 07806-5000

PROJ MGR

UNMANNED GROUND VEH

1 ATTN AMCPM UG
REDSTONE ARSENAL
AL 35898-8060

DIR

ARMY RSCH LAB

1 ATTN AMSRL CP PW
2800 POWDER MILL RD
ADELPHIA MD 20783-1145

VEHICLE PROPULSION DIR

1 ATTN AMSRL VP (MS 77 12)
NASA LEWIS RSCH CTR
21000 BROOKPARK RD
CLEVELAND OH 44135

CDR AMSAA

1 ATTN AMXSY CM
1 ATTN AMXSY L
APG MD 21005-5071

1	CDR ARO ATTN AMXRO EN (D MANN) RSCH TRIANGLE PK NC 27709-2211	1	PETROL TEST FAC WEST BLDG 247 TRACEY LOC DDRW P O BOX 96001 STOCKTON CA 95296-960
	DIR AMC PKG STO CONT CTR		CDR ARMY LEA
1	ATTN SDSTO TE S TOBYHANNA PA 18466-5097	1	ATTN LOEA PL NEW CUMBERLAND PA 17070-5007
	CDR AEC		CDR ARMY TECOM
1	ATTN SFIM AEC ECC (T ECCLES) APG MD 21010-5401	1	ATTN AMSTE TA R
	CDR ARMY ATCOM	1	ATTN AMSTE TC D
1	ATTN AMSAT I ME (L HEPLER)	1	ATTN AMSTE EQ APG MD 21005-5006
1	ATTN AMSAT I LA (V SALISBURY)		PROJ MGR PETROL WATER LOG
1	ATTN AMSAT R EP (V EDWARD) 4300 GOODFELLOW BLVD ST LOUIS MO 63120-1798	1	ATTN AMCPM PWL 4300 GOODFELLOW BLVD ST LOUIS MO 63120-1798
	CDR AVIA APPL TECH DIR		PROJ MGM MOBILE ELEC PWR
1	ATTN AMSAT R TP (H MORROW) FT EUSTIS VA 23604-5577	1	ATTN AMCPM MEP 7798 CISSNA RD STE 200 SPRINGFIELD VA 22150-3199
	CDR ARMY NRDEC		CDR ARMY COLD REGION TEST CTR
1	ATTN SATNC US (SIEGEL)	1	ATTN STECR TM
1	ATTN SATNC UE NATICK MA 01760-5018	1	ATTN STECR LG APO AP 96508-7850
	CDR ARMY ARDEC		CDR ARMY BIOMED RSCH DEV LAB
1	ATTN SMCAR CC	1	ATTN SGRD UBZ A FT DETRICK MD 21702-5010
1	ATTN SMCAR ESC S PICATINNY ARSENAL NJ 07808-5000		CDR FORSCOM
	CDR ARMY CRDEC	1	ATTN AFLG TRS FT MCPHERSON GA 30330-6000
1	ATTN SMCCR RS APG MD 21010-5423		CDR TRADOC
	CDR ARMY DESCOM	1	ATTN ATCD SL 5 INGALLS RD BLDG 163 FT MONROE VA 23651-5194
1	ATTN AMSDS MN		CDR ARMY ARMOR CTR
1	ATTN AMSDS EN CHAMBERSBURG PA 17201-4170	1	ATTN ATSB CD ML
	CDR ARMY AMCCOM	1	ATTN ATSB TSM T FT KNOX KY 40121-5000
1	ATTN AMSMC MA ROCK ISLAND IL 61299-6000		CDR ARMY QM SCHOOL
	CDR ARMY WATERVLIET ARSN	1	ATTN ATSM CD
1	ATTN SARWY RDD WATERVLIET NY 12189	1	ATTN ATSM PWD FT LEE VA 23001-5000
	DIR AMC LOG SPT ACT		CDR ARMY COMBINED ARMS SPT CMD
1	ATTN AMXLS LA REDSTONE ARSENAL AL 35890-7466	1	ATTN ATCL CD
	CDR APC	1	ATTN ATCL MS FT LEE VA 23801-6000
1	ATTN SATPC Q		
1	ATTN SATPC QE (BLDG 85 3) NEW CUMBERLAND PA 17070-5005		

1 CDR ARMY FIELD ARTY SCH
 1 ATTN ATSF CD
 FT SILL OK 73503

 CDR ARMY TRANS SCHOOL
 1 ATTN ATSP CD MS
 FT EUSTIS VA 23604-5000

 CDR ARMY INF SCHOOL
 1 ATTN ATSH CD
 1 ATTN ATSH AT
 FT BENNING GA 31905-5000

 CDR ARMY AVIA CTR
 1 ATTN ATZQ DOL M
 1 ATTN ATZQ DI
 FT RUCKER AL 36362-5115

 CDR ARMY CACDA
 1 ATTN ATZL CD
 FT LEAVENWORTH KA 66027-5300

 CDR ARMY ENGR SCHOOL
 1 ATTN ATSE CD
 FT LEONARD WOOD
 MO 65473-5000

 CDR ARMY ORDN CTR
 1 ATTN ATSL CD CS
 APG MD 21005

 CDR ARMY SAFETY CTR
 1 ATTN CSSC PMG
 1 ATTN CSSD SPS
 FT RUCKER AL 36362-5363

 CDR ARMY CSTA
 1 ATTN STECS EN
 1 ATTN STECS LI
 1 ATTN STECS AE
 1 ATTN STECS AA
 APG MD 21005-5059

 CDR ARMY YPG
 1 ATTN STEYP MT TL M
 YUMA AZ 85365-9130

 CDR ARMY CERL
 1 ATTN CECER EN
 P O BOX 9005
 CHAMPAIGN IL 61826-9005

 1 DIR
 AMC FAST PROGRAM
 10101 GRIDLEY RD STE 104
 FT BELVOIR VA 22060-5818

 CDR I CORPS AND FT LEWIS
 1 ATTN AFZH CSS
 FT LEWIS WA 98433-5000

CDR
 RED RIVER ARMY DEPOT
 1 ATTN SDSRR M
 1 ATTN SDSRR Q
 TEXARKANA TX 75501-5000

 PS MAGAZINE DIV
 1 ATTN AMXLS PS
 DIR LOGSA
 REDSTONE ARSENAL
 AL 35898-7466

 CDR 6TH ID (L)
 1 ATTN APUR LG M
 1060 GAFFNEY RD
 FT WAINWRIGHT
 AK 99703

DEPARTMENT OF THE NAVY

OFC OF NAVAL RSCH
 1 ATTN ONR 464
 800 N QUINCY ST
 ARLINGTON VA 22217-5660

 CDR
 NAVAL SEA SYSTEMS CMD
 1 ATTN SEA 03M3
 2531 JEFFERSON DAVIS HWY
 ARLINGTON VA 22242-5160

 CDR
 NAVAL SURFACE WARFARE CTR
 1 ATTN CODE 632
 1 ATTN CODE 859
 3A LEGGETT CIRCLE
 ANNAPOLIS MD 21401-5067

 CDR
 NAVAL RSCH LABORATORY
 1 ATTN CODE 6181
 WASHINGTON DC 20375-5342

 CDR
 NAVAL AIR WARFARE CTR
 1 ATTN CODE PE33 AJD
 P O BOX 7176
 TRENTON NJ 08628-0176

 1 CDR
 NAVAL PETROLEUM OFFICE
 CAMERON STA T 40
 5010 DUKE STREET
 ALEXANDRIA VA 22304-6180

 1 OFC ASST SEC NAVY (I 7 E)
 CRYSTAL PLAZA 5
 2211 JEFFERSON DAVIS HWY
 ARLINGTON VA 22244-5110

CDR
NAVAL AIR SYSTEMS CMD
1 ATTN AIR 53623C
1421 JEFFERSON DAVIS HWY
ARLINGTON VA 22243-5360

**DEPARTMENT OF THE NAVY
U.S. MARINE CORPS**

- HQ USMC
1 ATTN LPP
WASHINGTON DC 20380-0001
- 1 PROG MGR COMBAT SER SPT
MARINE CORPS SYS CMD
2033 BARNETT AVE STE 315
QUANTICO VA 22134-5080
- 1 PROG MGR GROUND WEAPONS
MARINE CORPS SYS CMD
2033 BARNETT AVE
QUANTICO VA 22134-5080
- 1 PROG MGR ENGR SYS
MARINE CORPS SYS CMD
2033 BARNETT AVE
QUANTICO VA 22134-5080

CDR
MARINE CORPS SYS CMD
1 ATTN SSE
2033 BARNETT AVE STE 315
QUANTICO VA 22134-5010

CDR
BLOUNT ISLAND CMD
1 ATTN CODE 922/1
814 RADFORD BLVD
JACKSONVILLE
FLA 32226-3404

- CDR
MARINE CORPS LOGISTICS BA
1 ATTN CODE 837
814 RADFORD BLVD
ALBANY GA 31704-1128

- 1 CDR
2ND MARINE DIV
PSC BOX 20090
CAMP LEJEUNNE
NC 28542-0090

- 1 CDR
1ST MARINE DIV
CAMP PENDLETON
CA 92055-5702

- 1 CDR
FMFPAC G4
BOX 64118
CAMP H M SMITH
HI 96861-4118

DEPARTMENT OF DEFENSE

- ODUSD
1 ATTN (L) MRM
PETROLEUM STAFF ANALYST
PENTAGON
WASHINGTON DC 20301-8000

- ODUSD
1 ATTN (ES) CI
400 ARMY NAVY DR
STE 206
ARLINGTON VA 22202

- HQ USEUCOM
1 ATTN ECJU L1J
UNIT 30400 BOX 1000
APO AE 09128-4209

- US CINCPAC
1 ATTN J422 BOX 64020
CAMP H M SMITH
HI 96861-4020

- 1 JOAP TSC
BLDG 780
NAVAL AIR STA
PENSACOLA FL 32408-5300

- DIR DLA
1 ATTN DLA MMDI
ATTN DLA MMSB
CAMERON STA
ALEXANDRIA VA 22304-6100

- CDR
DEFENSE FUEL SUPPLY CTR
1 ATTN DFSC Q BLDG 8
1 ATTN DFSC S BLDG 8
CAMERON STA
ALEXANDRIA VA 22304-6160

- CDR
DEFENSE GEN SUPPLY CTR
1 ATTN DGSC SSA
1 ATTN DGSC STA
8000 JEFFERSON DAVIS HWY
RICHMOND VA 23297-5678

- DIR ADV RSCH PROJ AGENCY
1 ATTN ARPA/ASTO
3701 N FAIRFAX DR
ARLINGTON VA 22203-1714

- 12 DEFENSE TECH INFO CTR
CAMERON STATION
ALEXANDRIA VA 22314

DEPARTMENT OF AIR FORCE

- HQ USAF/LGSSF
1 ATTN FUELS POLICY
1030 AIR FORCE PENTAGON
WASHINGTON DC 20330-1030

- 1 HQ USAF/LGTV
ATTN VEH EQUIP/FACILITY
1030 AIR FORCE PENTAGON
WASHINGTON DC 20330-1030

- AIR FORCE WRIGHT LAB
1 ATTN WL/POS
1 ATTN WL/POSF
1 ATTN WL/POSL
1790 LOOP RD N
WRIGHT PATTERSON AFB
OH 45433-7103

- AIR FORCE WRIGHT LAB
1 ATTN WL/MLBT
2941 P ST STE 1
WRIGHT PATTERSON AFB
OH 45433-7750

- AIR FORCE WRIGHT LAB
1 ATTN WL/MLSE
2179 12TH ST STE 1
WRIGHT PATTERSON AFB
OH 45433-7718

- 1 AIR FORCE MEEP MGMT OFC
615 SMSQ/LGTV MEEP
201 BISCAYNE DR STE 2
ENGLIN AFB FL 32542-5303

- 1 SA ALC/SFT
1014 ANDREWS RD STE 1
KELLY AFB TX 78241-5603

- 1 WR ALC/LVRS
225 OCMULGEE CT
ROBINS AFB
GA 31098-1647